



YachtCoatings
CHALLENGER PRO SE
TECHINCAL DATA SHEET

Product description

Challenger PRO Special Effect is a "Dual Layer" matte base that allows obtaining a metal and/or pearl finishing; a broad range of shades can be obtained through the use of the "ChallengerMix" tintometric system. When mixed with Hardener PRO 674.999, it boosts its reticulation to withstand the most severe weather and sea conditions. Challenger Pro SE must be covered with Challenger Pro Clear.

Product information

Product code	675		
Finish	Matt		
Colour	Colour card and tintometric system		
Solids (by volume)	ASTM D2369		30 ± 2%
Specific gravity	UNI EN ISO 2811-1		1,0 ÷ 1,1 g/cm ³
Flash point	UNI EN ISO 13736		23 – 55 °C
VOC (calculated average content)	ISO 11890-2/2006		436 g/l
Packaging	2 – 4 Lt		

Application and use

SURFACE PREPARATION

It is advisable to apply Challenger Pro SE on previously treated surfaces with Epoply and Undercoat Pro recommended undercoats. Sandpaper with P500 abrasive paper. Surfaces must be clean and properly prepared. Before painting, make sure that all surfaces are perfectly dry, clean and free from any trace of oil, grease and contaminants. Apply this topcoat on compatible undercoats, with a suitable and uniform colour.






APPLICATION PROCEDURE

The matte base, after being mixed with 10% of Hardener Pro 674.999, must be diluted at 50-70% with the thinner chosen on the basis of the ambient temperature. Apply two coats and then cover potential stains. When the surface is matte, it is advisable to apply a final coat lowering the air level of 1/2 bar and apply a light, uniform and regular coat keeping nearly 40 cm away from the surface.



YachtCoatings
CHALLENGER PRO SE
 TECHNICAL DATA SHEET



Application data

Mixing ratio by volume Base (comp. A) 675.--- Hardener (comp. B) 674.999		100 parts 10 parts
Pot-life NB: do not use this product when Pot-life time is exceeded		2 hrs at 20 °C
Thinner/Cleaning tools NB: the indicated dilution % is considered on the catalyzed product		15 – 25 °C Thinner PRO 698 (50 – 70% max) 22 – 35 °C Thinner PRO slow 697 (50 – 70% max)
Application methods		Conventional Pressure 3,5 bar Nozzle 1,3 mm N°2 wet on wet coverage + 1 low-pressure stain removing coat with intermediate "flash off"
		Air mixed Pressure 3,5 bar Nozzle 0,7 mm – 1,1 mm N°2 wet on wet coverage + 1 low-pressure stain removing coat with intermediate "flash off"
Dry film thickness per coat	Standard application range	20 – 30 µm
	Recommended	25 µm
Wet film thickness per coat	Standard application range	70 – 100 µm
	Raccommended	80 µm
Theoretical coverage	25 µm	12 m ² /l
Practical coverage (loss value 40%)	25 µm	7 m ² /l
Recommended primers	Epoply – Undercoat PRO	
Note	This product is provided in two tins to be mixed entirely and carefully before use. In case it is required, dilution has to be performed after the mixing of the two components. The physical data of two-component products refer to components that have been already mixed.	



YachtCoatings
CHALLENGER PRO SE
 TECHNICAL DATA SHEET

Drying time

Temperature °C	10		15		20		30	
	Min	Max	Min	Max	Min	Max	Min	Max
Wet on wet coverage 			30'	180'	20'	120'	15'	90'
Coverage with transparent 			2 h	24 h	1 h	24 h	1 h	18 h

N.B. *The drying times and the overcoating intervals increase with higher thickness of the applied film. Always check that the existing painting film is perfectly dry before applying a further product coat.*

CONDITIONS DURING APPLICATION

In order to avoid the formation of condensation, the surface temperature should be at least 3 °C above dew point. During application and curing, the min. ambient temperature must not be lower than 15°C or higher than 30 °C; substrate temperature must not be lower than 10 °C, since curing is remarkably reduced at lower temperatures.

Application is recommended when the relative humidity is within the range of 30 - 80%. The term-hygrometric survey should be carried out near the surface to be coated. Make sure there is enough ventilation when the application takes place in closed areas.

Storage

It is recommended to avoid exposure to air and extreme temperatures. To maximize the shelf life in the can, it is worth checking that the container is well closed during the storage and the temperature is between 10 °C and 35 °C. Avoid exposure to direct sunlight.



YachtCoatings
CHALLENGER PRO SE
TECHINCAL DATA SHEET

Safety rules

Comply with the provisions set by the local health and safety at work regulations. Operate in well ventilated places and, if in closed areas, use vacuum cleaners, fans and air conveyors. During the application use appropriate protections (masks, gloves, glasses, etc.). Before using, read sections 7-8 of the SDS.

INSTRUCTIONS FOR THE DISPOSAL OF PRODUCTS AND PACKAGING

Empty packaging that contained products: Dispose of empty packaging according to the requirements of the waste disposal law, for example by taking them to the recycling center.

Packages containing the unused products: Dispose of the unused product in accordance with the law of disposal of such waste, for example by taking it to a recycling center, recycling of packaging is prohibited in this case. Do not empty into drains or watercourses. Product packaging must be kept indoor, and the temperature in the storage place must be between 10 °C and 35 °C. Do not expose to sunlight.

Notes

The values indicated in the present technical sheet can have slight variations from one batch to another. All data refer to the mixed product. The applied product must not come in contact with water, chemicals or subjected to mechanical stress before the curing is complete. The wet film thicknesses refer to the undiluted product. With dilution this value will rise. The above information is the result of accurate laboratory tests and practical experience; however, since the product is predominantly used outside the manufacturer's control, Boero Bartolomeo S.p.A. can only guarantee its quality. The information contained in this sheet may be subject to revision by the Company. For clarification, updates or further information, it is recommended to contact Boero Bartolomeo S.p.A. directly. The present datasheet annuls and replaces every other precedent to this one.



YachtCoatings
CHALLENGER PRO SE
TECHINICAL DATA SHEET

Recommendations

This material has been tested and meets all batch quality requirements. Colours produced in different times, thought with the help of modern technologies, may show variation in shades; however, ΔE values remain within the accepted parameters. The application of different batches in the last enamel coat should be avoided. Be careful to apply the product also on elements, such as doors or grills, that are usually treated in different times and with different methods. Please, follow the procedures specified by Boero Bartolomeo S.p.A when it comes to revision and waxing. Boero Bartolomeo S.p.A accepts no liability for any issues concerning any difference in shade.