

# FISHERMAR

700.637

## Description

One-component alkyd topcoat with good coverage, colour retention and brush application properties.

## Use

Glossy topcoat for above waterline paint systems, suitable for brush and spray application, with a good range of colours. For exterior and interior areas with mildly to moderately corrosive environment.

## Informations

Finish	Glossy	
Colours	.001 White - .400 Light Blue - .116 Dark Blue - .064 Light Grey - .359 Dark Grey - .201 Black - .180 Red	
Pack	0,5 (only .001 White) – 2,5 l	
Solids by Volume	40 ± 2% (white) 58 ± 2% (colours)	ISO 3233-2
Specific Gravity	1,20 ÷ 1,25 g/cm <sup>3</sup> (white and derived colours) 1,05 ÷ 1,10 g/cm <sup>3</sup> (other colours)	ISO 2811-1
Flash Point	39 °C	ISO 3679
VOC	334 g/l	Calculated
Shelf Life	36 months	

## Application




### SURFACE PREPARATION

All surfaces must be clean, dry and free of contaminants before application of recommended products. Existing paint/materials must be dry, undamaged and compatible. Supplied air for surface preparation and cleaning must be dry and clean.

### COATED SURFACES

**Primers and Undercoats:** clean, dry and undamaged compatible primers or undercoats. If overcoating times are exceeded, provide superficial rugosity to ensure proper adhesion.

## How to Apply

Standard		Brush and roller
Conventional Spray		Pressure 3,5 bar Nozzle 1,2 – 1,4 mm
Airless		Not recommended

## Film Thickness per Coat

DFT	Recommended: 40 µm Standard application range: 35 - 45 µm
WFT	Recommended: 100 µm (white) - 70 µm (colours) Standard application range: 90 - 100 µm (white), 60 – 80 µm (colours)

# FISHERMAR

700.637

## Additional Application Information

<b>Theoretical spreading rate</b>	Application range at the recommended thickness: 40 µm – 10 m <sup>2</sup> /l (white), 14,5 m <sup>2</sup> /l (colours)
<b>Thinner</b>	703 – Roller/Brush (10% max) 703 – Conventional spray (10% max)
<b>Notes</b>	Thoroughly stir the product. Extra thinning will result in lower film build and slower drying. Total thickness per coat to be achieved in 2/3 wet on wet coats

## Compatibility

### Previous Coat

Noxy, Giano, Defender

### Subsequent Coat

N.A.

## Drying Time

	10 °C		15 °C		20 °C		30 °C	
	Min	Max	Min	Max	Min	Max	Min	Max
<b>Overcoating interval</b>	N.A.	N.A.	32 h	7 days	24 h	7 days	18 h	7 days
<b>Complete drying</b>	N.A.	N.A.	7 days	7 days	7 days	7 days	5 days	5 days

N.B. The drying times and the overcoating intervals increase with higher thickness of the applied paint film. Always check the existing paint film is dry before applying any further product coats.

## Conditions during application

During application and curing:

Ambient temperature: minimum 15 °C, maximum 35 °C.

Minimum substrate temperature 10 °C (if during the curing the temperature drops below 10 °C, overcoating will take additional time).

Avoid the formation of condensation, the surface temperature should be at least 3 °C above dew point.

Maximum relative humidity 85%.

Painting area should be well ventilated, during application and drying/curing.

## Storage

It is recommended to avoid exposure to air and extreme temperatures. To maximize the shelf life in the can, check that the container is closed during the storage and the temperature is between 5 °C and 35 °C.

Avoid exposure to direct sunlight.

## Safety Rules

Comply with the provisions set by the local health and safety at work regulations. Avoid contact with the skin, operate in well-ventilated places and, if in closed areas, use vacuum cleaners, fans and air conveyors. During the application use appropriate PPE - Personal Protections Equipment (masks, gloves, glasses, etc.). Before using, read sections 7-8 of the SDS

### INSTRUCTIONS FOR THE DISPOSAL OF THE BIOCIDAL PRODUCTS AND PACKAGING

Empty packaging containing biocidal products: disposal of empty packaging according to the requirements of the waste disposal law, for example by taking them to the recycling centre. Packages containing the unused biocidal product: Dispose of the product not used in accordance with the law of disposal of such waste, for example by taking it to a recycling centre, recycling of packaging is prohibited in this case. Do not empty into drains or watercourses.

# FISHERMAR

700.637

## INSTRUCTIONS FOR THE SAFETY SECURITY OF THE BIOCIDAL PRODUCTS AND PACKAGING

Empty containers and containers still containing the biocidal product: Packaging must be disposed of as hazardous waste under the full responsibility of the holder of such waste. Do not empty into drains or watercourses.

### Disclaimer

The values indicated in the present technical sheet can have slight variations from one batch to another. The applied product must not come in contact with water, chemicals or subjected to mechanical stress before the curing is complete. The wet film thickness refers to the undiluted product. In case of dilution, this value increases. The above information is the result of accurate laboratory tests and practical experience, however, since the product is predominantly used outside the manufacturer's control, Boero Bartolomeo S.p.A. can only guarantee their quality. The information contained in this sheet may be subject to revision by the Company. For clarification, updates or further information, it is recommended to contact Boero Bartolomeo S.p.A. directly. The present datasheet annuls and replaces every other precedent to this one.