

CHALLENGERPRO MIX RATIOS

FUSION	BASE P672 1	HARDENER P674 1	THINNER P698/7 15% 35%	
SUPERYACHT	BASE P680 2	HARDENER P690/674 1	THINNER P698/7 25% 45%	
YACHT	BASE P673 2	HARDENER P690/674 1	THINNER P698/6/7 25% 45%	
BRUSH	BASE P679 3	HARDENER P679 1	THINNER P694 5% 15%	
MATT	BASE P683 2	HARDENER P674 1	THINNER P698/7 20%	
BASECOAT	BASE P677 10	HARDENER P674 1	THINNER P698/7 40% 50%	
BASECOAT SE	BASE P675 10	HARDENER P674 1	THINNER P698/7 60% 70%	
CLEAR	BASE P690.200 2	HARDENER P690 1	THINNER P698/7 25% 40%	
CLEAR MATT	BASE P690.100 3	HARDENER P690 1	THINNER P698/7 50%	